



G&E Blended Chlorobutyl

G&E Blended Chlorobutyl is produced by carefully combining selected feedstocks for uniform viscosity and rheology. G&E Blended Chlorobutyl is excellent for cost reduction in applications such as innerliners and most mechanical goods when blended with prime chlorobutyl.

TYPICAL CHEMICAL PROPERTIES

Mooney Viscosity (ML 1+8 @ 125°C)	35 ± 10
Raw Polymer Specific Gravity	0.92
Chlorine Content	1.1 ± 0.2
Volatile Matter, % weight	1.0 max.

TYPICAL PHYSICAL PROPERTIES (CURE 40 @ 150°C)

Tensile, psi	1900
Elongation, %	400
300% modulus, psi	1000

PACKAGING

Thirty, 75 lb. (34 kg.) bales wrapped in low-melt polyethylene film are packaged in corrugated boxes on heat-treated pallets weighing approximately 2,200 lbs. (1 MT) each. Material is also available in returnable metal boxes.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.

1/10/14