



Blended Polymers

G&E Blended EPDM 374

G&E Blended EPDM 374 is produced from feedstocks carefully selected for uniform viscosity, ethylene propylene ratio and 3rd monomer. The feedstocks are chosen to produce a blended EPDM Polymer which has a high ethylene content, medium mooney and medium diene. G&E Blended EPDM 374 can be blended with prime EPDM polymers to reduce compound costs.

TYPICAL COMPOUND PROPERTIES

Mooney Viscosity (ML 1+4 @ 125°C)	30 ± 10
Raw Polymer Specific Gravity	0.86
Volatile Matter, % weight	1 max.
Ethylene Content	High
3rd Monomer	Medium

PACKAGING

Each low-melt polyethylene bag contains 33lbs. of 3/8" diameter free flowing pellets. There are forty-two bags per shipping box. Each shipping box measures 61" x 45" x 32" and weighs approximately 1,386 lbs. net.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.

2/23/16