



Blended Polymers

G&E Blended EPDM 465-75

G&E Blended EPDM 465-75 is produced from feedstocks carefully selected for uniform viscosity, ethylene propylene ratio and 3rd monomer. G&E 465-75 EPDM polymer has a medium ethylene content, medium mooney and medium diene and contains 75 parts non-staining oil. G&E Blended 465-75 can be blended with prime EPDM polymers to reduce compound costs.

TYPICAL COMPOUND PROPERTIES

Mooney Viscosity (ML 1+4 @ 125°C)	45 ± 10
Raw Polymer Specific Gravity	0.86
Volatile Matter, % weight	1.0 max.
Ethylene Content	Medium
3rd Monomer	Medium
Non-Staining Oil	75 parts

PACKAGING

Twenty-four, 75 lb. (34 kg.) bales wrapped in low-melt polyethylene. Packaged in corrugated boxes on heat-treated pallets of approximately 1,800 lbs. (.816 MT) each.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.

1/10/14