



G&E Blended Butyl and Halogenated Rubber

Goldsmith & Eggleton's reprocessed rubber significantly reduces customer material and part costs when used in conjunction with virgin polymers or on a stand-alone basis.

Manufactured under tightly controlled processing standards, our reprocessed rubber products exhibit a consistency of performance and reliability that is trusted throughout the world

G&E GRADE	MOONEY VISCOSITY 1+8 @ 125°C	UNSATURATION	HALOGEN
G&E Blended Butyl	40 ± 10	Medium	—
G&E Blended Bromobutyl	35 ± 10	—	2.0 ± 0.6
G&E Blended Chlorobutyl	35 ± 10	—	1.1 ± 0.2
G&E Blended PMSB	40 ± 10	—	0.9 - 2.0
G&E Blended HIIR	40 ± 15	—	0.7 - 2.1

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.

