



## Specification Sheet

### G&E Blended Bromobutyl

G&E Blended Bromobutyl is produced by carefully selected feedstocks for uniform viscosity and rheology. G&E Blended Bromobutyl is excellent for cost reduction in all types of bromobutyl applications when used as a direct partial replacement for prime bromobutyl.

#### **Typical Chemical Properties**

Raw Polymer Viscosity (ML 1+8 at 125°C)	34 ± 10
Raw Polymer Specific Gravity	0.93
Volatile Matter, % weight	1 max

#### **Typical Physical Properties (cure 40' @ 150°C)**

Tensile, psi	1700
Elongation, %	400
300% Modulus, psi	1200

#### **Packaging**

Thirty, 75 lb. bales wrapped in low-melt polyethylene. Shipped in 61" X 45" X 32" boxes of approximately 2,250 lbs. net each.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.