



Specification Sheet

G&E Blended Butyl

G&E Blended Butyl is produced by carefully selected feedstocks for uniform viscosity and rheology. G&E Blended Butyl is excellent for cost reduction in all types of butyl applications when used as a partial replacement for prime butyl.

Typical Chemical Properties

Mooney Viscosity (ML 1+8 at 125°C)	38 ± 10
Raw Polymer Specific Gravity	0.92
Volatile Matter, % weight	1 max

Typical Physical Properties (cure 40' @ 150°C)

Tensile, psi	2400
Elongation, %	575
300% Modulus, psi	1200

Packaging

Thirty, 75 lb. bales wrapped in low-melt polyethylene. Shipped in 61" X 45" X 32" boxes of approximately 2,250 lbs. net each.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.