



Specification Sheet

G&E Blended Chlorobutyl

G&E Blended Chlorobutyl is produced by carefully selected feedstocks for uniform viscosity and rheology. G&E Blended Chlorobutyl is excellent for cost reduction in applications such as innerliners, and most mechanical goods when used as a partial replacement of prime Chlorobutyl.

Typical Chemical Properties

Raw Polymer Viscosity (ML 1+8 at 125°C)	35 ± 10
Raw Polymer Specific Gravity	0.92
Volatile Matter, % weight	1 max

Typical Physical Properties (cure 40' @ 150°C)

Tensile, psi	1900
Elongation, %	400
300% Modulus, psi	1000

Packaging

Thirty, 75 lb. bales wrapped in low-melt polyethylene. Shipped in 61" X 45" X 32" boxes of approximately 2,250 lbs. net each.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.