



## **G&E BLENDED EPDM 465-75**

G&E Blended EPDM 465-75 is produced from feedstocks carefully selected for uniform viscosity, ethylene propylene ratio and 3<sup>rd</sup> monomer. G&E 465-75 EPDM polymer has a medium ethylene content, medium mooney and medium unsaturation and contains 75 parts non-staining oil. G&E 465-75 can be blended with prime EPDM polymers to reduce compound costs.

### **TYPICAL PROPERTIES**

Mooney Viscosity (ML 1+4 @ 125°C)	45 ± 10
Raw Polymer Specific Gravity	0.86
Volatile Matter, % weight	1 max.
Ethylene Content	Medium
3rd Monomer	Medium
Non Staining Oil	75 Parts

### **PACKAGING**

Twenty-four, 75 lb. (34 kg.) bales wrapped in low-melt polyethylene. Packaged in corrugated boxes on heat-treated pallets of approximately 1,800 lbs. (.816 MT) each.

*The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.*