



## Specification Sheet

### G&E Blended EPDM 465-75

G&E Blended EPDM 465-75 is produced from feedstocks carefully selected for uniform viscosity, ethylene propylene ratio and 3<sup>rd</sup> monomer. G&E 465-75 EPDM polymer has a medium ethylene content, medium mooney and medium unsaturation and contains 75 parts non-staining oil. G&E Blended EPDM 465-75 can be blended with prime EPDM polymers to reduce compound costs.

#### **Typical Properties**

Mooney Viscosity (ML 1+4 at 125°C)	42 ± 10
Raw Polymer Specific Gravity	0.86
Volatile Matter, % weight	1 max
Ethylene Content	Medium
3rd monomer	Medium
Non Staining Oil	75 Parts

#### **Packaging**

Thirty, 75 lb. bales wrapped in low-melt polyethylene. Shipped in 61" X 45" X 32" boxes of approximately 2,250 lbs. net each.

*The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.*