



Reliable Polymer Alternatives

Blended Polymers

G&E BLENDED EPDM 565

G&E Blended EPDM 565 is made from feedstocks carefully selected for uniform viscosity, ethylene propylene ratio and 3rd monomer. G&E 565 polymer has a high ethylene content, medium mooney and medium unsaturation. G&E 565 can be blended with prime EPDM polymers to reduce compound costs in extruded, calendered and molded applications.

TYPICAL PROPERTIES

Mooney Viscosity (ML 1+4 @ 125°C)	50
Raw Polymer Specific Gravity	0.88
Volatile matter, % weight	1.0 max.
Ethylene Content	High
3rd Monomer	Medium

PACKAGING

Material is produced in 55 lb. bales (25 kg) packaged in a corrugated box on heat-treated pallets each weighing approximately 2,000 lbs. (.91 MT). Free flowing pellets in bulk Gaylord type boxes available upon request.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.