



## Specification Sheet

### G&E Blended EPDM 565

G&E Blended EPDM 565 is made from feedstock from various suppliers. The feedstocks are chosen to produce a blended EPDM polymer which has a high ethylene content, medium mooney and medium unsaturation. G&E Blended EPDM 565 can be blended with prime EPDM polymers to reduce compound costs in extruded, calendered and molded applications.

#### **Typical Properties**

Mooney Viscosity (ML 1+4 at 125°C)	50 ± 10
Raw Polymer Specific Gravity	0.88
Volatile Matter, % weight	1 max
Ethylene Content	High
3rd monomer	Medium

#### **Packaging**

Each low-melt polyethylene bag contains 33 lbs of 3/8" diameter free flowing pellets. There are forty-two bags per shipping box. Each shipping box measures 61" X 45" X 32" and weighs approximately 1,386 lbs. net.

*The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.*