



## Specification Sheet

### G&E Blended EPDM 674

G&E Blended EPDM 674 is produced from feedstocks carefully selected for uniform viscosity, ethylene propylene ratio and 3<sup>rd</sup> monomer. G&E 674 EPDM polymer has a high ethylene content, medium mooney and medium unsaturation. G&E Blended EPDM 674 can be blended with prime EPDM polymers to reduce compound costs in extruded, calendered and molded applications where high green strength is critical.

#### **Typical Properties**

Mooney Viscosity (ML 1+4 at 125°C)	60 ± 10
Raw Polymer Specific Gravity	0.86
Volatile Matter, % weight	1 max
Ethylene Content	High
3rd monomer	Medium

#### **Packaging**

Each low-melt polyethylene bag contains 33 lbs. of 3/8" diameter free flowing pellets. There are forty-two bags per shipping box. Each shipping box measures 61" X 45" X 32" and weighs approximately 1,386 lbs. net.

*The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.*