



G&E BLENDED HALOGENATED BUTYL

G&E Blended Halogenated Butyl is produced by carefully combining selected feedstocks for uniform viscosity and halogen content. G&E Blended Halogenated Butyl is excellent for cost reductions in applications such as non-cured tapes, construction adhesives and caulks. G&E Blended Halogenated Butyl can be used as a direct partial replacement of prime Butyl and halogenated Butyl rubber.

TYPICAL CHEMICAL PROPERTIES

Mooney Viscosity (ML 1+8 @ 125°C)	40 ± 15
Raw Polymer Specific Gravity	0.93 typical
Volatile Matter, % weight	1 max.
Halogen	0.70 – 2.1

PACKAGING

Thirty, 75 lb. (34 kg.) bales wrapped in low-melt polyethylene film are packaged in corrugated boxes on heat-treated pallets weighing approximately 2,200 lbs. (1 MT) each. Material is also available in returnable metal boxes.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.