



Specification Sheet

G&E PMSB

G&E Blended PMSB is made from brominated isobutylene paramethylstyrene feedstock selected for mooney, bromine, and paramethylstyrene content to achieve uniformly blended polymer. G&E PMSB can be used to replace prime bromobutyl or prime brominated isobutylene paramethylstyrene where cost reduction is needed.

Typical Chemical Properties

Mooney Viscosity (ML 1+4 at 125°C)	45 ± 10
Raw Polymer Specific Gravity	0.93
Volatile Matter, % weight	1 max

Packaging

Thirty, 75 lb. bales wrapped in low-melt polyethylene. Shipped in 61" X 45" X 32" boxes of approximately 2,250 lbs. net each.

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.