

## G&E 1815 Black Masterbatch Technical Data Sheet

G&E 1815 BMB is mechanically mixed SBR Black masterbatch. This material can be used to replace SBR-1815 coprecipitated masterbatch in most applications. G&E 1815 contains 100 parts of non-staining SBR, 75 parts of N-300 series carbon black, and 50.0 parts Napthenic Oil.

### TYPICAL COMPOUND SPECIFICATIONS

#### MILLED MOONEY VISCOSITY

ASTM D 1646	ML 1+4@100°C	60-80
-------------	--------------	-------

#### ODR RHEOMETER

	ASTM D 2084	12 Minutes/3° Arc@ 177°C
ML	6.5	
MH	36	
Ts2	2.2	
Tc90	7	

#### TYPICAL PHYSICAL PROPERTIES

	ASTM D 412	Cured 35 Min @ 145°C
Tensile, psi	2200	
Elongation, %	575	
300 % Modulus, psi	950	
Specific Gravity	1.14	

#### TEST RECIPE

	ASTM D 3186	Mill Mixed
1815 BMB	225 pts.	
Zinc Oxide	3.00 pts.	
Stearic Acid	1.50 pts.	
Sulfur	1.75 pts.	
TBBS	1.25 pts.	

#### PACKAGING

Standard Package: Approximately 30"x38"x3/8" slabs on a 4-way entry skid, approximately 2,200 lbs. net (1 Metric Ton). Boxes are shipped on heat treated wood it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implemented.

*The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.*

9/19/17