

## G&E Blended Halobutyl Technical Data Sheet

G&E Blended Halogenated Butyl is produced by carefully combining selected feedstocks for uniform viscosity and halogen Content. G&E Blended Halogenated Butyl is excellent for cost reductions in applications such as non-cured tapes, construction adhesives, caulks, inner liners, and re-treader sundries. G&E Blended Halogenated Butyl can be used as a direct partial replacement of prime Butyl and halogenated Butyl Rubber.

### TYPICAL COMPOUND SPECIFICATIONS

#### MOONEY VISCOSITY

ASTM D 1646	ML 1+8@125°C (257°F)	30-50
ASTM F 970	Raw Polymer specific Gravity	0.93
G&E Method	XRF Total Halogen Content, %	0.7-2.1
ASTM D 5667 -95	(% Ash Content)	2 Maximum
ASTM D 5668	(Volatile Matter, % weight)	1 Maximum

#### PACKAGING

Thirty-six, 75 lb. (34 kg.) bales wrapped in low-melt polyethylene film are packaged in Returnable Metal Boxes weighing 2,700 lbs (1.23 MT) each.

*The information contained herein is based upon laboratory test results believe to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implemented.*

09/25/18