



Blended Polymers

G&E Blended EPDM 254

G&E Blended EPDM 254 is produced from feedstocks carefully selected for uniform viscosity, ethylene propylene ratio, and 3rd monomer. The feedstocks are chosen to produce a blended EPDM Polymer which has a medium ethylene content, medium diene content, and low mooney. G&E Blended EPDM 254 can be blended with prime EPDM polymers to reduce compound costs in extruded, calendered and molded applications.

TYPICAL COMPOUND SPECIFICATIONS

Mooney Viscosity (ML 1+4 @ 125°C)	29 ±10
Raw Polymer Specific Gravity	0.86
Volatile Matter, wt%	1.0 max
Ethylene Content, wt%	57 ± 5
ENB Content, wt%	Medium

PACKAGING

55 lb. (25 kg.) bales are wrapped in low melt polyethylene film and are packaged in Returnable Metal Boxes, weighing approximately 2,600 lbs. (1.18 MT) each

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.

09/25/18

