

## Blended Oil-Extended Solution SBR

Blended Oil Extended S-SBR is manufactured from feedstocks carefully selected to produce uniform viscosity oil-extended SSBR. The material can be used in a blend with prime polymers to reduce compound costs in tires, tread rubber, conveyor belts, extruded and molded general technical rubber articles.

### TYPICAL PROPERTIES

Mooney Viscosity (ML 1+4 @ 100°C)	45 ± 10
AEM Non-Aromatic Oil	37.5 phr
Raw Polymer Specific Gravity	0.95
Volatile Matter, wt%	≤ 1%
Stabilizer	Staining
Styrene	25.5%
Vinyl	24%

### PACKAGING

Thirty, 75 lb. bales wrapped in low-melt polyethylene. Shipped in 61" x 45" x 32" boxes of approximately 1 metric ton each.

*The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.*

09/25/18